

**TECHNICAL DATA****FIX-PM(PV)**Polyethylene-cellfoam with closed cells, self adhesive

---

<b>Property</b>		<b>Test Method</b>	<b>Value</b>
Color			anthracite or white
Adhesive			synthetic rubber hot-melt
Liner			without, fixed siliconized foil
Peel adhesion		DIN EN 1939	material break
Density		ISO 845	~30 kg/m <sup>3</sup>
Water absorption (7d)			< 1 % vol
Resistance to high humidity			very good
Temperature range			-30 °C +80 °C
Tensile strength	lengthwise	ISO 1926	325 kPa
	crosswise	ISO 1926	220 kPa
Compressive strength at 50% compression		ISO 844	98 kPa
Elongation at break	lengthwise	ISO 1926	125 %
	crosswise	ISO 1926	115 %
Compression set (25% / 22 h at 23 °C; 24 h after discharge		ISO 1856-B	12 %
	0,5 h after discharge		20 %

*The information supplied is accurate to the best of knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where proprietary or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form of any contract with a customer.*

---